



HIGH PERFORMANCE VpCI™ COATINGS

VpCI-329 D



PRODUCT DESCRIPTION

VpCI-329 D is a ready-to-use vapor corrosion inhibiting oil-based rust preventive. VpCI-329 D provides excellent protection to metals in indoor and outdoor sheltered conditions. VpCI-329 D protects in two unique ways. First, oil-soluble corrosion inhibitors offer a tenacious film which clings to metal surfaces, providing excellent contact corrosion protection. In addition to this film barrier, VpCI-329 D releases vapor phase corrosion inhibitors into the air that attach electrochemically to the metal surface.

FEATURES

- Performs effectively even under the adverse conditions of 100% relative humidity and in the presence of such corrosive species as chlorides, hydrogen sulfide or other sulfur compounds
- High flash and fire points
- Contains no hazardous chromates, nitrites or phosphate inhibitors
- Provides universal corrosion protection to ferrous and non-ferrous metals
- Non-toxic and thermally stable, providing long-lasting contact and vapor phase corrosion protection
- VpCI-329 D is a special version of VpCI-329 that is diluted 1:9 and is ready-to-use

METHOD OF APPLICATION

VpCI-329 D can be sprayed, dipped, rolled on or brushed onto metal surfaces.

VpCI-329 D is great for protecting metal parts that require a light coat of oil for further processing and shipment, such as gears, spindles, coils, or any other metal part that uses oil for corrosion protection.

TYPICAL PROPERTIES

Appearance	Hazy to opaque yellow to tan liquid
Carrier	Light naphthenic oil
Coverage	960-1450 ft ² /gal (24-36 m ² /l)
Drying Time	Remains tacky
Film Thickness (dry film)	1-1.5 mils (25-37.5 microns)
Film Type	Oily
Flash Point	295°F (146°C)
Non-volatile Content	87-97%
Odor	Petroleum
pH	9-10 (1% in water)
Removal Method	Petroleum solvents / alkaline cleaners (VCI-410 series)
Density	7.3-7.5 lb/gal (0.87-0.90 kg/l)

PACKAGING AND STORAGE

VpCI-329 D is packaged in 5 gallon (19 liter) plastic pails, 55 gallon (208 liter) metal drums, liquid totes and bulk.

VpCI-329 D should be stored sealed. Agitate before each use. The shelf life is 24 months in sealed containers.

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT MATERIAL SAFETY DATA SHEET FOR
MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Distributed by:



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.cortecvci.com>

printed on recycled paper  10% post consumer
Revised 5/2/06. ©Cortec Corporation 1998-2006. All rights reserved. Supersedes: 3/9/06.
© 1998-2006, Cortec Corporation. All Rights Reserved. Copying of these materials in any form
without the written authorization of Cortec Corporation is strictly prohibited.