

# **VpCI®-372 Peelable Coating**

#### **DESCRIPTION**

VpCI®-372 is a fast drying, water-based acrylic peelable coating that provides protection in sheltered applications. Provides multi-metal protection. Excellent UV resistance. Can be matched to some custom colors.

#### **PACKAGING & STORAGE**

VpCI®-372 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) metal drums, liquid totes, and bulk. Keep product from freezing.

Product shelf life is 1 year.



# **CHARACTERISTICS/TECHNICAL DATA**

| Volume Solids                | 33.40%  |
|------------------------------|---|
| Gloss (ASTM D532)            | NA  |
| VOCs (ASTM D3960)            | 0.2 lbs/gal (24 g/l)                                  |
| Viscosity                    | 50-70 sec # 3 Zahn Cup                                |
| Pencil Hardness (ASTM D3363) | NA  |
| Spreading Rate               | 536 sq.ft./gal @ 1.0 mils DFT<br>(13.15 sq.m/l@25 µm) |
| Weight per Gallon            | 8.85 lbs/gal (1.06 kg/l)                              |
| Flash Point                  | >200°F (93°C)   |
| Recommended DFT              | 2.0-10.0 mils (50-250 μm)                             |
| Recommended WFT              | 6.0-30.0 mils (150-750 μm)                            |
| Dry to Touch                 | 1-2 hrs   |
| Dry to Handle                | 2-3 hrs   |
| Recoat Time                  | NA  |
| Force Dry                    | 15-20 min @ 150°F (65°C)                              |
| Full Cure                    | 3-7 days  |
| Salt Spray (ASTM B117)       | 168 hrs   |
| Humidity (ASTM D1748)        | 168 hrs   |
| Adhesion (ASTM D3359)        | NA  |
| Flexibility (ASTM D522)      | 1/2" mandrel (1.27cm)                                 |

<sup>\*</sup>All tests performed after a 7 day cure at ambient temperature

# **VpCI®-372 Peelable Coating**

#### **APPLICATION**

# **Surface Preparation**

Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, rust inhibitors, or any other surface contamination that could affect adhesion. For structural steel applications, Cortec® recommends a minimum of a NACE #3/SSPC-SP6 commercial blast clean. Consult Cortec® and/or test system adhesion prior to full scale application.

Note: Make sure dew point is more than 5°F (2°C) less than air temperature for application. Power agitate to a uniform consistency using a "squirrel cage" type mixer, hand-held drill mixer, or other equivalent method. VpCI®-372 can be applied by spray, roll, brush, or dip.

# **Typical Equipment Set Ups**

#### **HVLP / Conventional Spray**

- Tip .009"-.021" \*dependent upon pressures and viscosity
- Air Pressure 45-55 psi
- Fluid Pressure 10 psi
- Fluid hose should be 3/8" (0.95 cm) I.D. with a maximum length of 50 feet (15.2 m). Pot should always have dual regulation and be kept at same elevation as spray gun.

#### **Air Assisted Airless / Airless**

- Tip .015"-.035" \*dependent upon pressures and viscosity
- Pressure 1800-2500 psi
- Hose should be 3/8" (0.95 cm) I.D. minimum, but a ¼" (0.64 cm) I.D. whip end section may be used for ease of application. A maximum length of 100 feet (30.5 m) is suggested.

#### Clean Up

Clean tools/equipment immediately after use with water when coating is still wet. When dry, simply peel off.

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT SAFETY DATA SHEET FOR MORE
INFORMATION

4119 White Bear Parkway, St. Paul, MN 55110 USA Phone (651) 429-1100, Fax (651) 429-1122 Toll Free (800) 4-CORTEC info@cortecvci.com http://www.cortecvci.com http://www.corteccoatings.com











### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.